

PU SANDING SEALER 6889022

DESCRIPTION

- Polyurethane Sealer provides very good sealing and sanding properties with a good transparency and flow, as well as a quick drying properties and a good resistance to subsequent top coats.

PHYSICAL DATA

Viscosity (Roto thinner)	:	5-6 poise
S.G (mixed)	:	0.97
Volume solid	:	approx 30 %
Spreading rate	:	12 m ² /liter @25 microns DFT
Surface dry@30C	:	15 mts@25 microns DFT
Hard Dry	:	2 hrs
Sanding	:	after 30 minutes
Pot Life	:	approx 4 Hours at 30° C

APPLICATION

Application method	:	air spray or air less spray
Mixing ratio	:	6889022(sealer) : 100 parts 591 9221 (catalyst) : 50 parts Thinner 5669155 : 20-25 parts (for air spray) : 5-10 parts (for airless spray)

USAGE

- Suitable as a sealer for any kind of wood

Surface preparations

- Wood should be fully dried and free from natural oils. Apply by spray both horizontally and vertically; the second coat after 1 hour from the first one. Sanding between the two coats is must to obtain optimum surface finish.