

## PAINTCO CHLORINATED RUBBER FINISH 54

### DESCRIPTION

- Paintco Chlorinated Rubber Finish is chlorinated rubber based glossy paint, suitable as a topcoat for interior and exterior exposure. This fast drying coating is resistant to splash of mild chemical and mineral oils. This product is suitable as finish coat on suitably primed metal and concrete surfaces. It has fire retarding, antibacterial and fungicidal properties.

### PHYSICAL DATA

Pigment	:	Rutile titanium dioxide and / or color pigments
Appearance	:	Glossy
Colours	:	White & colors
Specific gravity	:	Approx. 1.24
Solids by volume	:	Approx. 34%
Drying time at 30°C	:	Dust dry : approx. 30 minutes Hard dry : approx. 8 hours Recoatibility : after 8 hours
Flash Point	:	26°C

### APPLICATION DATA

Application method	:	Airless spray, air spray, brush and roller.
Airless spray data	:	Nozzle 0.013, pressure 110-150kg/cm <sup>2</sup>
Type of thinner	:	Thinner no. 32
Percentage of thinner	:	Airless spray : 5% max by volume Air spray : 10% max. by volume Brush & Roller : 3% max. By volume
Dry film thickness per coat	:	35 microns per coat
Theor. Coverage @ 35microns DFT	:	9.7 m <sup>2</sup> /litre

### Surface Condition

Surfaces to be painted should be dry and free from contamination.

### Priming Coats

- For steel surfaces: Apply Paintco Chlorinated Primer 58.
- For nonferrous surfaces: Apply Paintco Etch Primer /2pack 3255.
- For concrete surfaces: Apply Paintco Chlorinate Rubber Finish 54 with 25% thinning by using thinner no. 32 to ensure good penetration (Self Priming).