

PAINTCO CHLORINATED RUBBER PRIMER 58

DESCRIPTION

- Paintco Chlorinated Rubber Primer Coating is a self priming fast drying with excellent anticorrosive properties. This product is resistant to splash of mild chemicals & mineral oils.

PHYSICAL DATA

Pigments	:	Rutile titanium dioxide and / or color pigments and functional extenders.
Appearance	:	flat
Colours	:	White & colours
Specific gravity	:	Approx. 1.40
Solids by volume	:	Approx. 40%
Drying time at 30°C	:	Dust dry : approx. ≤ 10 minutes Hard dry : approx. 8 hours Recoatibility : after 8 hours
Flash point	:	25°C

APPLICATION DATA

Recommended substrate conditions	:	Steel blast cleaned to Sa 2.5 or power tool cleaned to St2. Surface temperature should be at least 3°C above dew point. Concrete properly cured and free from alkalinity & contaminations.
Application method	:	Airless spray, air spray, brush and roller
Thinner type	:	No. 32
Airless spray data	:	Nozzle size 0.018", pressure 150kg/cm ²
Thinner percentage	:	Airless spray : 3% max. by volume Air spray : 10% max by volume Brush and roller : 5% max by volume
Dry film thickness	:	60 microns
Theor. coverage @ 60 microns DFT	:	6.6m ² /ltr

REMARKS

- This product is also suitable for concrete and has fire retardant, antibacterial and fungicidal properties.