TECHNICAL DATA الحجانات الفنية



PAINTCO ULTRA PRIMER / 2 K 28526

DESCRIPTION

· Paintco Ultra Primer 2 K is a premium fast drying, high build primer surface especially formulated for use with Ultra H.S/2K top coats in automotive refinish. Main feature of this products is easily sanding and excellent adhesion to properly prepared surfaces and minimum settling of the thinned primer in the spray pot overnight.

PHYSICAL DATA

Pigments Rutile titanium dioxide and /or color

pigments and functional extenders.

Appearance matt

Colour white & grey

No. of components Two

Mixing ratio by volume Base: Hardener

3

Pot life after mixing at 30°C 6 hours

Specific gravity Approx. 1.3 (mixed.) Solids by volume Approx. 43% (mixed.) Drying times at 30°C surface dry : 30 min

Dry to sand approx 60mts depending on film build and

ambient conditions

Flash point 21°C

APPLICATION DATA

Application method Airless spray or air spray Type of Thinner Ultra Thinner 326

Percentage of thinner

Airless spray : 3-5% max. by volume

Air spray : 25 % max. by volume

Application Viscosity 17-20 sec Recommended DFT per coat 40 microns

Theor. coverage at 40 microns DFT: Approx. 10.75 m2 / litre

REMARKS

Not to be applied below 5oC and /or above relative humidity of 80%