

## PAINTCO HIGH GLOSS ENAMEL 1226

### DESCRIPTION

- Excellent gloss and colour retention, good intercoat adhesion as well as film integrity of High Gloss Enamel after prolonged exposure are the outcome of modification in the chemical structure of binder combined with U.V. resistance pigments. It complies with SASO's Standard for Enamel Paints.
- Suitable for application on wood ,steel, cement and plaster surfaces coated with adequate primer for interior and exterior use.

### PHYSICAL DATA

Pigment	:	Titanium dioxide and /or colour pigments
Appearance	:	High gloss
Colours	:	White and colours
Specific gravity	:	Approx. 1.12
Solids by volume	:	Approx. 46%
Drying time at 30°C	:	Dust dry : approx. 2 hours Hard dry : approx. 8 hours Recoatibility : overnight
Flash point	:	39°C.

### APPLICATION DATA

Application method	:	Air spray, airless spray , brush and roller
Airless spray data	:	Nozzle 0.011, pressure 150kg /cm <sup>2</sup>
Type of thinner	:	Thinner No. 211
Percentage of thinner	:	Airless spray : 5% max. by volume Air spray : 15% max. by volume Brush & roller : 10% Max. by volume
Dry film thickness per coat	:	30 microns
Ther. Coverage @ 30 mic. DFT	:	15.3 m <sup>2</sup> / litre

### Priming coats

- For cement and plaster surfaces: Paintco Latex Primer Sealer 1201.
- For steel surfaces : Metal Primer 3010
- For nonferrous surfaces : Etch Primer / 2PK 3255 followed by Metal Primer 3010.
- For wood surfaces : Paintco Wood & Wall Primer 1333.
- Airless spray information is subject to adjustment and is for guidance only.