

PAINTCO LATEX UNDERCOAT 1222

DESCRIPTION

- Paintco Latex Undercoat is based on adhesion promoting alkali resistant copolymer. It is ideal as a dual purposes sealing / covering undercoat for interior and exterior concrete or plastered walls. It is recommended that it should be covered with suitable Paintco finishes.

PHYSICAL DATA

Pigments	:	Titanium/or colour pigments and functional extenders
Appearance	:	Flat
Colours	:	White and colours
No. of components	:	One
Specific gravity	:	Approx. 1.48
Solids by volume	:	Approx. 33%
Drying time at 30°C	:	Dust dry : approx. 30 minutes Hard dry : approx. 1 hour Next coat : after 2 hours
Flash point	:	Nonflammable

APPLICATION DATA

Application method	:	Airless spray , air spray , brush & roller
Type of thinner	:	Sweet water
Percentage of thinner	:	Airless spray : 5% max. by volume Air spray : 10% max. by volume Brush & roller : 5% max. by volume.
Dry film thickness per coat	:	30 microns.
Theor. coverage at 30 microns DFT	:	11 m ² / litre

Surface preparation

- The surface should be free from grit, dirt and grease. Fill minor cracks and voids with Paintco Magna Wall Filler 10000 (for interior) and Paintco Magna Spray Plaster Putty 20000 (for exterior). Sand with sand paper lightly and thereafter apply Paintco Latex Undercoat 1222.

Subsequent Coats

- Paintco Exterior or Interior Acrylic Emulsion Finish (Matt, Semigloss or gloss) OR Paintco Smoothtex Structure Finish.
- OR Paintco Magnatex Structure Finish (Fine or Medium)
- OR Paintco Spray Plaster Structure Finish (1-1.5mm or 2 mm)
- Clean all tools with water immediately after use.