TECHNICAL DATA الحجانات الفنية



PAINTCO ULTRA / 2 K 6652

DESCRIPTION

· Paintco Ultra 2 K is a two pack acrylic resin based enamel cured with aliphatic polyisocyanate. This product is suitable for car refinish ,primed steel, pretreated non ferrous metals.. Paintco Ultra / 2k exhibits excellent gloss and color retention, film integrity, chemical and abrasion resistance and excellent resistance to weathering.

PHYSICAL DATA

Pigments Rutile titanium dioxide and /or color

pigments and functional extenders.

Appearance Glossy

Colour clear, White and colours

No. of components Two

Mixing ratio by volume Base : Hardener

2

Pot life after mixing at 30°C 6 hours

Specific gravity Approx. 1.00 (mixed.) Solids by volume Approx. 43% (mixed.) Drying times at 30°C surface dry : 30 min : 12 hours Hard dry

Next coat: after 16 hours

Flash point 21°C

APPLICATION DATA

Application method Airless spray or air spray

Type of Thinner ultra thinner (slow or fast depend on weather)

Percentage of thinner Airless spray : 3-5% max. by volume Air spray : 10% max. by volume

17-20 sec

Application Viscosity Recommended DFT per coat 40 microns

Theor. coverage at 30 microns DFT: Approx. 10.75 m2 / litre

REMARKS

Not to be applied below 5°C and /or above relative humidity of 80%.